

무방향성 전기강판 (Non-grain oriented electrical steel)

두께 mm (inch)	POSCO		JIS C 2552		ASTM A677		EN10106	
	(2018) W/kg 15/50		(2014) W/kg 15/50		(2016) W/kg 15/60		(2016) W/kg 15/50	
0.35 (0.0138)	35PN 210	2.10	35A210	2.10	36F145	3.20	M210-35A	2.10
	35PN 230	2.30	35A230	2.30	36F155	3.42	M235-35A	2.35
	35PN 250	2.50	35A250	2.50	36F165	3.64	M250-35A	2.50
	35PN 270	2.70	35A270	2.70	36F175	3.86	M270-35A	2.70
	35PN 300	3.00	35A300	3.00	36F185	4.08	M300-35A	3.00
	35PN 330	3.30	35A330	3.30	36F195	4.30	M330-35A	3.30
	35PN 360	3.60	35A360	3.60	36F205	4.52	-	-
	35PN 440	4.40	35A440	4.40				
0.50 (0.0197)	50PN 250	2.50	50A250	2.50			M250-50A	2.50
	50PN 270	2.70	50A270	2.70			M270-50A	2.70
	50PN 290	2.90	50A290	2.90	47F165	3.64	M290-50A	2.90
	50PN 310	3.10	50A310	3.10	47F180	3.97	M310-50A	3.10
	50PN 330	3.30	50A330	3.30	47F190	4.19	M330-50A	3.30
	50PN 350	3.50	50A350	3.50	47F200	4.41	M350-50A	3.50
	50PN 400	4.00	50A400	4.00	47F210	4.63	M400-50A	4.00
	50PN 470	4.70	50A470	4.70	47F240	5.29	M470-50A	4.70
	50PN 600	6.00	50A600	6.00	47F280	6.17	M600-50A	6.00
	50PN 700	7.00	50A700	7.00	47F400	8.82	M700-50A	7.00
	50PN 800	8.00	50A800	8.00	47F450	9.92	M800-50A	8.00
	50PN 1000	10.00	50A1000	10.00			M940-50A	9.40
	50PN 1300	13.00	50A1300	13.00			-	-
0.65 (0.0256)	65PN 310	3.10	65A310	3.10	64F200	4.41	M310-65A	3.10
	65PN 350	3.50	65A350	3.50	64F210	4.63	M350-65A	3.50
	65PN 400	4.00	65A400	4.00	64F225	4.96	M400-65A	4.00
	65PN 470	4.70	65A470	4.70	64F235	5.18	M470-65A	4.70
	65PN 600	6.00	65A600	6.00	64F250	5.51	M600-65A	6.00
	65PN 700	7.00	65A700	7.00	64F275	6.06	M700-65A	7.00
	65PN 800	8.00	65A800	8.00	64F320	7.05	M800-65A	8.00
	65PN 1000	10.00	65A1000	10.00	64F500	11.02	M1000-65A	10.00
	65PN 1300	13.00	65A1300	13.00	64F550	12.13	-	-